

HYDROLOCK 2

Rev: June 2019

**Structural
Waterproofing**

JUTA UK HYDROLOCK 2 - Is a Mechanically bonded Geosynthetic Clay Liner (GCL) composite of pulverised bentonite embedded between two layers of geotextile with an LLDPE membrane fixed to one side. The internal 5kg of natural sodium bentonite swells in contact with water to form a low permeability waterproofing barrier, with the membrane forming an impermeable barrier which will restrict the flow of ground gas.

JUTA UK HYDROLOCK 2 when used with 150 mm properly-designed concrete, is satisfactory for use as a fully-bonded Type A waterproofing protection as defined in BS 8102: 2009 for the waterproofing of new structures. JUTA UK HYDROLOCK can be used externally on concrete to provide an effective barrier to the transmission of liquid water where Grades 1 to 3 waterproofing protection are required as defined in Table 2 of BS 8102 : 2009.

JUTA UK HYDROLOCK 2			
Characteristic	Test Method	Unit	HYDROLOCK 2
Geotextile Layers			
Carrier Layer (PP Woven) MPUA	EN ISO 9864	g/m ²	100
Cover Layer (PP Non-Woven) MPUA	EN ISO 9864	g/m ²	200
PE membrane	EN ISO 9863-1/-2	mm	0.2
Bentonite (Sodium Bentonite) LAYER			
Montmorillonite Content	CUR 33 (VDG 69)	%	>75
Swell Index	ASTM D 5890	ml/2g	≥24
Fluid Loss	ASTM D 5891	ml	<18
Moisture Content	DIN 18121-1	%	<12
Water Absorption	DIN 18132	%	>500
Geosynthetic Clay Liner			
Mass per unit area of Bentonite	EN 14196	g/m ²	5000
Mass per unit area of Bentonite	EN 14196	g/m ²	5500
Thickness	EN ISO 9863-1/-2	mm	>7.5
Tensile Strength (MD/CMD)	EN ISO 10319	kN/m	10.5/10.5
Permeability	ASTM D 5887	m/s	No flow
Index Flux	ASTM D 5887	m ³ /m ² /s	No flow
Grab Tensile Strength	ASTM 4632	N	>400
CBR puncture Resistance	EN ISO 12236	kN	>2.0
Peel Strength	ASTM D 6496	N/10cm	>60
Water Tightness	EN 1928 (60kPa)	-	PASS (Impermeable)
Water Vapour Transmission	EN 1931 (B)	g/m ² /s	2.35 X 10 ⁻⁵
Peel adhesion to concrete	ASTM D 903 (mod)	kN/m	5.3
Roll Dimensions			
Roll Width x Length	Typical	m	1.25 x 5.0
Roll Area	Typical	m ²	6.25

Contact us to find out more information
info@juta.co.uk | 01772 754177 | JUTA.CO.UK
 Melton Grove Works, Church Road, Lytham, FY8 5PL

JUTA



riba
product
selector

Additional Information

HANDLING

Roll weights can be in excess of 20kg and hence appropriate care and equipment is required for unloading and handling.

STORAGE

Rolls of HYDROLOCK 2 should be stored on stable/level ground and stacked not more than five rolls high, with no other material stacked on top. The rolls can be stored outdoors when packaged, but should be protected from exposure to UV.

INSTALLATION

HYDROLOCK 2 should be installed in accordance with the product installation guidelines.

JOINTING AND SEALING

HYDROLOCK 2 should be jointed and sealed in accordance with the product installation guidelines.

ACCESSORY PRODUCTS

Accessory bentonite is provided with each load of HYDROLOCK 2 to assist with jointing and sealing. Additional bentonite is available on request. Accessories also include:

- HYDROLOCK STRIP
- HYDROLOCK PASTE
- HYDROLOCK RAIL

PLEASE CONTACT JUTA UK DIRECTLY FOR MORE INFORMATION ON HYDROLOCK.