

HYDROLOCK POWDER

Rev: June 2019

Structural
Waterproofing

JUTA UK HYDROLOCK POWDER - Is supplied in 20kg bags, and is pulverised bentonite used as an accessory to the HYDROLOCK GCL liner, or used separately as a high grade Natural Sodium Bentonite.

JUTA UK HYDROLOCK POWDER			
Characteristic	Test Method	Unit	HYDROLOCK
Bentonite (Sodium Bentonite) Bags 20kg			
Montmorillonite Content	CUR 33 (VDG 69)	%	> 75
Swell Index	ASTM D 5890	ml/2g	≥ 24
Fluid Loss	ASTM D 5891	ml	< 18
Moisture Content	DIN 18121-1	%	1 - 6
Water Absorption	DIN 18132	%	> 450
pH 10% Suspension	-	-	9 - 11
Granulation	PN-83/H-10077	mm	0.0 - 1.0

HANDLING

HYDROLOCK Powder is supplied in bags of 20kg and hence appropriate care and equipment is required for unloading and handling.

STORAGE

Bags of HYDROLOCK powder should be stored on stable/level ground with no other material stacked on top. The bags can be stored outdoors when packaged.

PLEASE CONTACT JUTA UK DIRECTLY FOR MORE INFORMATION ON HYDROLOCK.

Contact us to find out more information
info@juta.co.uk | 01772 754177 | JUTA.CO.UK
Melton Grove Works, Church Road, Lytham, FY8 5PL



riba
product
selector

JUTA